



US009650837B2

(12) **United States Patent**
Patel et al.

(10) **Patent No.:** **US 9,650,837 B2**
(45) **Date of Patent:** **May 16, 2017**

(54) **MULTI-CHAMFER CUTTING ELEMENTS HAVING A SHAPED CUTTING FACE AND EARTH-BORING TOOLS INCLUDING SUCH CUTTING ELEMENTS**

(71) Applicant: **Baker Hughes Incorporated**, Houston, TX (US)

(72) Inventors: **Suresh G. Patel**, The Woodlands, TX (US); **David A. Stockey**, The Woodlands, TX (US); **Alejandro Flores**, Spring, TX (US); **Anthony A. DiGiovanni**, Houston, TX (US); **Danny E. Scott**, Montgomery, TX (US); **Leroy W. Ledgerwood, III**, Cypress, TX (US)

(73) Assignee: **BAKER HUGHES INCORPORATED**, Houston, TX (US)

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 251 days.

(21) Appl. No.: **14/480,293**

(22) Filed: **Sep. 8, 2014**

(65) **Prior Publication Data**
US 2016/0069140 A1 Mar. 10, 2016

(51) **Int. Cl.**
E21B 10/46 (2006.01)
E21B 10/54 (2006.01)
(Continued)

(52) **U.S. Cl.**
CPC **E21B 10/5673** (2013.01); **B24D 18/00** (2013.01); **B24D 99/005** (2013.01);
(Continued)

(58) **Field of Classification Search**
CPC E21B 10/5673; E21B 10/43; E21B 10/55; E21B 10/46; E21B 10/54;
(Continued)

(56) **References Cited**

U.S. PATENT DOCUMENTS

4,224,380 A 9/1980 Bovenkerk et al.
4,538,690 A 9/1985 Short
(Continued)

FOREIGN PATENT DOCUMENTS

CN 2278759 Y 4/1998
CN 2579580 Y 10/2003
(Continued)

OTHER PUBLICATIONS

Chinese Office Action for Chinese Application No. 201180026366.0 dated Apr. 29, 2014.


(Continued)

Primary Examiner — Cathleen Hutchins
(74) *Attorney, Agent, or Firm* — TraskBritt

(57) **ABSTRACT**

A cutting element for an earth-boring tool includes a substrate and volume of superabrasive material positioned on the substrate. The volume of superabrasive material includes a cutting face having at least one recess extending into the volume of superabrasive material and/or at least one protrusion extending outward from the volume of superabrasive material. The volume of superabrasive material includes a first chamfer surface having a peripheral edge and a radially innermost edge. The peripheral edge of the first chamfer surface is located proximate a cutting edge of the volume of superabrasive material. A radial width of the first chamfer surface is between about 0.002 inch and about 0.045 inch. The volume of superabrasive material also includes a second chamfer surface having a peripheral edge and a radially innermost edge. The peripheral edge of the second chamfer surface is located adjacent the radially innermost edge of the first chamfer surface.

15 Claims, 11 Drawing Sheets



(51) **Int. Cl.**
E21B 10/56 (2006.01)
E21B 10/567 (2006.01)
E21B 10/55 (2006.01)
B24D 99/00 (2010.01)
E21B 10/43 (2006.01)
B24D 18/00 (2006.01)
C23C 16/27 (2006.01)

(52) **U.S. Cl.**
 CPC *E21B 10/43* (2013.01); *E21B 10/55* (2013.01); *C23C 16/27* (2013.01)

(58) **Field of Classification Search**
 CPC E21B 2010/545; E21B 2010/561; E21B 10/56; E21B 2010/562
 See application file for complete search history.

(56) **References Cited**
 U.S. PATENT DOCUMENTS

4,539,018	A	9/1985	Whanger	7,363,992	B2	4/2008	Stowe et al.
4,558,753	A	12/1985	Barr	7,373,998	B2	5/2008	Cariveau et al.
4,593,777	A	6/1986	Barr	7,533,740	B2	5/2009	Zhang et al.
4,629,373	A	12/1986	Hall	7,740,090	B2	6/2010	Shen et al.
4,858,707	A	8/1989	Jones et al.	7,814,998	B2	10/2010	Patel et al.
4,872,520	A	10/1989	Nelson	7,861,808	B2	1/2011	Zhang et al.
4,984,642	A	1/1991	Renard et al.	8,016,054	B2	9/2011	Lancaster et al.
4,997,049	A	3/1991	Tank et al.	8,061,456	B2	11/2011	Patel et al.
5,007,207	A	4/1991	Phaal et al.	8,191,656	B2	6/2012	Dourfaye et al.
5,027,912	A	7/1991	Juergens	8,210,288	B2	7/2012	Chen et al.
5,054,246	A	10/1991	Phaal et al.	8,684,112	B2	4/2014	DiGiovanni et al.
5,078,219	A	1/1992	Morrell et al.	8,739,904	B2	6/2014	Patel
5,127,923	A	7/1992	Bunting et al.	D712,941	S	9/2014	Mo
5,172,778	A	12/1992	Tibbitts	8,833,492	B2	9/2014	Durairajan et al.
5,333,699	A	8/1994	Thigpen	2002/0071729	A1	6/2002	Middlemiss et al.
5,351,772	A	10/1994	Smith	2004/0009376	A1	1/2004	Wan et al.
5,355,969	A	10/1994	Hardy et al.	2005/0247492	A1	11/2005	Shen et al.
5,377,773	A	1/1995	Tibbitts	2005/0269139	A1	12/2005	Shen et al.
5,437,343	A	8/1995	Cooley et al.	2006/0201712	A1	9/2006	Zhang et al.
5,447,208	A	9/1995	Lund et al.	2007/0235230	A1	10/2007	Cuillier et al.
5,449,048	A	9/1995	Thigpen et al.	2008/0006448	A1	1/2008	Zhang et al.
5,533,582	A	7/1996	Tibbitts	2008/0035380	A1	2/2008	Hall et al.
5,549,171	A	8/1996	Mensa et al.	2008/0164071	A1	7/2008	Patel et al.
5,569,000	A	10/1996	Llittecke et al.	2008/0264696	A1	10/2008	Dourfaye et al.
5,607,024	A	3/1997	Keith	2008/0308321	A1	12/2008	Aliko et al.
5,653,300	A	8/1997	Lund et al.	2009/0008155	A1	1/2009	Sherwood, Jr.
5,881,830	A	3/1999	Cooley	2009/0057031	A1	3/2009	Patel et al.
5,890,552	A	4/1999	Scott et al.	2009/0114628	A1	5/2009	DiGiovanni
5,944,129	A	8/1999	Jensen	2009/0260877	A1	10/2009	Wirth
5,967,250	A	10/1999	Lund et al.	2009/0321146	A1	12/2009	Dick et al.
5,984,005	A	11/1999	Hart et al.	2010/0084198	A1	4/2010	Durairajan et al.
6,006,846	A	12/1999	Tibbitts et al.	2010/0104874	A1	4/2010	Yong et al.
6,045,440	A	4/2000	Johnson et al.	2010/0276200	A1	11/2010	Schwefe et al.
6,050,354	A *	4/2000	Pessier E21B 10/16 175/425	2010/0288564	A1	11/2010	Dovalina, Jr. et al.
6,059,054	A	5/2000	Portwood et al.	2010/0307829	A1	12/2010	Patel
6,065,554	A	5/2000	Taylor et al.	2010/0326741	A1	12/2010	Patel
6,068,071	A	5/2000	Jurewicz et al.	2010/0326742	A1	12/2010	Vempati et al.
6,145,608	A	11/2000	Lund et al.	2011/0000714	A1	1/2011	Durairajan et al.
6,164,394	A	12/2000	Mensa-Wilmot et al.	2011/0031030	A1	2/2011	Shen et al.
6,187,068	B1	2/2001	Frushour et al.	2011/0031031	A1	2/2011	Vempati et al.
6,196,340	B1	3/2001	Jensen et al.	2011/0031036	A1	2/2011	Patel
6,196,910	B1	3/2001	Johnson et al.	2011/0088950	A1	4/2011	Scott et al.
6,202,770	B1	3/2001	Jurewicz et al.	2011/0171414	A1	7/2011	Sreshta et al.
6,202,771	B1	3/2001	Scott et al.	2011/0259642	A1	10/2011	DiGiovanni et al.
6,220,376	B1	4/2001	Lundell	2011/0303466	A1	12/2011	DiGiovanni
6,328,117	B1	12/2001	Berzas et al.	2012/0037431	A1	2/2012	DiGiovanni et al.
6,450,271	B1	9/2002	Tibbitts et al.	2012/0205162	A1	8/2012	Patel et al.
6,524,363	B2	2/2003	Gates, Jr. et al.	2013/0068534	A1 *	3/2013	DiGiovanni E21B 10/5673 175/428
6,527,065	B1	3/2003	Tibbitts et al.	2013/0068537	A1	3/2013	DiGiovanni
6,550,556	B2	4/2003	Middlemiss et al.	2013/0068538	A1	3/2013	DiGiovanni et al.
6,935,444	B2	8/2005	Lund et al.	2013/0292188	A1	11/2013	Bilen et al.
6,962,218	B2	11/2005	Eyre	2014/0238753	A1	8/2014	Nelms et al.
7,000,715	B2	2/2006	Sinor et al.	2014/0246253	A1 *	9/2014	Patel E21B 10/5673 175/430
7,188,692	B2	3/2007	Lund et al.				

FOREIGN PATENT DOCUMENTS

CN	1714224	A	12/2005
CN	201024900	Y	2/2008
CN	201202408	Y	3/2009
EP	546725	A1	9/1996
EP	835981	A2	4/1998
EP	656458	B1	2/1999
EP	979699	A1	2/2000
WO	9415058	A1	7/1994
WO	9427769	A1	12/1994
WO	0048789	A1	8/2000
WO	0160554	A1	8/2001
WO	2008006010	A3	5/2008

OTHER PUBLICATIONS

Russian Office Action for Russian Application No. 2012 149 79 dated Feb. 13, 2015.
 Chinese Office Action and Search Report for Chinese Application No. 201280051840 dated May 27, 2015, 15 pages.

(56)

References Cited

OTHER PUBLICATIONS

Guilin Color Engineered Diamond Technology (EDT) Co. Ltd., Brochure, Offshore Technology Conference Apr. 30-May 3, 2012.
Guilin Star Diamond Superhard Material Co. Ltd., Brochure, Offshore Technology Conference Apr. 30-May 3, 2012.

Pilkey in Peterson's Stress Concentration Factors (2d ed., Wiley Interscience 1997), in Section 2.6.6, on p. 71 (1997).

Patel et al., U.S. Appl. No. 14/480,293 entitled, Multi-Chamfer Cutting Elements Having a Shaped Cutting Face, Earth-Boring Tools Including Such Cutting Elements, and Related Methods, filed Sep. 8, 2014.

International Search Report for International Application No. PCT/US2015/048840 dated Nov. 30, 2015, 3 pages.

International Written Opinion for International Application No. PCT/US2015/048840 dated Nov. 30, 2015, 9 pages.

* cited by examiner




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8




FIG. 9




FIG. 10




FIG. 11




FIG. 12




FIG. 13




FIG. 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18




FIG. 19




FIG. 20




FIG. 21

1

**MULTI-CHAMFER CUTTING ELEMENTS
HAVING A SHAPED CUTTING FACE AND
EARTH-BORING TOOLS INCLUDING SUCH
CUTTING ELEMENTS**

CROSS-REFERENCE TO RELATED
APPLICATIONS

The subject matter of this patent application is related to the subject matter of U.S. patent application Ser. No. 13/092,396, filed Apr. 22, 2011, now U.S. Pat. No. 8,684,112, issued on Apr. 1, 2014, to DiGiovanni et al.; and to the subject matter of U.S. patent application Ser. No. 13/472,377, filed as May 15, 2012, now U.S. Pat. No. 9,482,057, issued on Nov. 1, 2016, to DiGiovanni et al.; and to the subject matter of U.S. patent application Ser. No. 13/477,905, filed May 22, 2012, now U.S. Pat. No. 9,243,452, issued on Jan 26, 2016, to DiGiovanni et al.; and to the subject matter of U.S. patent application Ser. No. 13/840,195, filed Mar. 15, 2013, now U.S. Pat. No. 9,428,966, issued on Aug. 30, 2016, to Patel et al.; and to the subject matter of U.S. patent application Ser. No. 13/609,575, filed Sep. 11, 2012, now U.S. Pat. No. 9,103,174, issued on Aug. 11, 2015, to DiGiovanni; and to the subject matter of U.S. patent application Ser. No. 13/461,388, filed May 1, 2012, now U.S. Pat. No. 8,991,525, issued on Mar. 31, 2015, to Bilén et al.; and to the subject matter of U.S. Pat. No. 6,935,444, issued on Aug. 30, 2005, to Lund et al.; and to the subject matter of U.S. Pat. No. 6,145,608, issued on Nov. 14, 2000, to Lund et al.; and to the subject matter of U.S. Pat. No. 5,437,343, issued on Aug. 1, 1995, to Cooley et al., the entire disclosure of each of which is incorporated herein by this reference.

TECHNICAL FIELD

Embodiments of the present disclosure relate to earth-boring tools, cutting elements for such earth-boring tools, and related methods.

BACKGROUND

Wellbores are formed in subterranean formations for various purposes including, for example, extraction of oil and gas from the subterranean formation and extraction of geothermal heat from the subterranean formation. Wellbores may be formed in a subterranean formation using a drill bit such as, for example, an earth-boring rotary drill bit. Different types of earth-boring rotary drill bits are known in the art including, for example, fixed-cutter bits (which are often referred to in the art as “drag” bits), rolling-cutter bits (which are often referred to in the art as “rock” bits), diamond-impregnated bits, and hybrid bits (which may include, for example, both fixed cutters and rolling cutters). The drill bit is rotated and advanced into the subterranean formation. As the drill bit rotates, the cutters or abrasive structures thereof cut, crush, shear, and/or abrade away the formation material to form the wellbore. A diameter of the wellbore drilled by the drill bit may be defined by the cutting structures disposed at the largest outer diameter of the drill bit.

The drill bit is coupled, either directly or indirectly, to an end of what is referred to in the art as a “drill string,” which comprises a series of elongated tubular segments connected end-to-end that extends into the wellbore from the surface of the formation. Often various tools and components, including the drill bit, may be coupled together at the distal end of the drill string at the bottom of the wellbore being drilled.

2

This assembly of tools and components is referred to in the art as a “bottom-hole assembly” (BHA).

The drill bit may be rotated within the wellbore by rotating the drill string from the surface of the formation, or the drill bit may be rotated by coupling the drill bit to a downhole motor, which is also coupled to the drill string and disposed proximate the bottom of the wellbore. The downhole motor may comprise, for example, a hydraulic Moineau-type motor having a shaft, to which the drill bit is mounted, that may be caused to rotate by pumping fluid (e.g., drilling mud or fluid) from the surface of the formation down through the center of the drill string, through the hydraulic motor, out from nozzles in the drill bit, and back up to the surface of the formation through the annular space between the outer surface of the drill string and the exposed surface of the formation within the wellbore.

BRIEF SUMMARY

This summary does not identify key features or essential features of the claimed subject matter, nor does it limit the scope of the claimed subject matter in any way.

In some embodiments, the present disclosure includes a cutting element for an earth-boring tool including a substrate and a volume of superabrasive material positioned on the substrate. The volume of superabrasive material includes a cutting face having one or more of at least one recess extending into the volume of superabrasive material and at least one protrusion extending outward from the volume of superabrasive material. The volume of superabrasive material includes a first chamfer surface having a peripheral edge and a radially innermost edge. The peripheral edge of the first chamfer surface is located proximate a cutting edge of the volume of superabrasive material. A radial width of the first chamfer surface, measured between the peripheral edge and the radially innermost edge of the first chamfer surface in a plane transverse to a longitudinal axis of the cutting element, is between about 0.002 inch and about 0.045 inch. The volume of superabrasive material also includes a second chamfer surface having a peripheral edge and a radially innermost edge. The peripheral edge of the second chamfer surface is located adjacent the radially innermost edge of the first chamfer surface.

In other embodiments, the present disclosure includes an earth-boring tool having at least one cutting element affixed to a tool body of the earth-boring tool. The at least one cutting element includes a volume of superabrasive material positioned on a substrate. The volume of superabrasive material includes a cutting face having one or more of at least one recess extending into the volume of superabrasive material and at least one protrusion extending outward from the volume of superabrasive material. The volume of superabrasive material includes a first chamfer surface having a peripheral edge and a radially innermost edge. The peripheral edge of the first chamfer surface is located proximate a cutting edge of the volume of superabrasive material. A radial width of the first chamfer surface, measured between the peripheral edge and the radially innermost edge of the first chamfer surface in a plane transverse to a longitudinal axis of the cutting element, is between about 0.002 inch and about 0.045 inch. The volume of superabrasive material also includes a second chamfer surface having a peripheral edge and a radially innermost edge. The peripheral edge of the second chamfer surface is located adjacent the radially innermost edge of the first chamfer surface.

BRIEF DESCRIPTION OF THE DRAWINGS

While the specification concludes with claims particularly pointing out and distinctly claiming what are regarded as

embodiments of the present disclosure, various features and advantages of this disclosure may be more readily ascertained from the following description of example embodiments of the disclosure provided with reference to the accompanying drawings.

FIG. 1 illustrates a perspective view of an earth-boring drill bit with blades carrying cutting elements, according to an embodiment of the present disclosure.

FIG. 2 illustrates a perspective view of a multi-chamfer cutting element having a cutting face with a recess therein, according to an embodiment of the present disclosure.

FIG. 3 illustrates a partial cross-sectional side view of the multi-chamfer cutting element of FIG. 2.

FIG. 4 illustrates a partial cross-sectional side view of a multi-chamfer cutting element having an arcuate recessed surface in a cutting face thereof, according to an embodiment of the present disclosure.

FIG. 5 illustrates a perspective view of a multi-chamfer cutting element having a planar recessed surface in a cutting face thereof, according to an embodiment of the present disclosure.

FIG. 6 illustrates a partial cross-sectional side view of the multi-chamfer cutting element of FIG. 5.

FIG. 7 illustrates a partial cross-sectional side view of a multi-chamfer cutting element having a centrally located protrusion extending upward from a planar recessed surface.

FIG. 8 is a graph of test results illustrating the durability of various cutting elements.

FIG. 9 illustrates a side elevation view of a worn single-chamfer cutting element charted in the graph of FIG. 8.

FIG. 10 illustrates a front elevation view of the worn cutting element of FIG. 9.

FIG. 11 illustrates a side elevation view of a worn dual-chamfer cutting element charted in the graph of FIG. 8.

FIG. 12 illustrates a front elevation view of the worn cutting element of FIG. 11.

FIG. 13 illustrates a side elevation view of an additional worn dual-chamfer cutting element charted in the graph of FIG. 8.

FIG. 14 illustrates a front elevation view of the worn cutting element of FIG. 13.

FIG. 15 illustrates a cross-sectional side view of a multi-chamfer cutting element having a conical protrusion extending upward from a recessed surface of a cutting face of the cutting element, according to an embodiment of the present disclosure.

FIG. 16 illustrates a cross-sectional side view of a multi-chamfer cutting element having a conical protrusion extending upward from a flat surface of the cutting face of the cutting element, according to an embodiment of the present disclosure.

FIG. 17 illustrates a front elevation view of a cutting face of a multi-chamfer cutting element, wherein a portion of the cutting face is polished, according to an embodiment of the present disclosure.

FIG. 18 illustrates a front elevation view of a cutting face of a multi-chamfer cutting element, wherein a portion of the cutting face is polished to influence flow of formation cuttings toward a lateral side of the cutting face as the cutting element engages a subterranean formation, according to an embodiment of the present disclosure.

FIG. 19 illustrates a front elevation view of a cutting face of a multi-chamfer cutting element configured to generate two (2) distinct streams of formation cuttings flowing to opposing lateral sides of the cutting face, wherein a portion of the cutting face is polished to reduce the average size of

formation cuttings in the two (2) discrete streams, according to an embodiment of the present disclosure.

FIG. 20 illustrates a partial cross-sectioned side view of an embodiment of an earth-boring tool utilizing selective placement of multi-chamfer cutting elements, according to an embodiment of the present disclosure.

FIG. 21 illustrates a bottom view of an earth-boring tool depicting selective placement of multi-chamfer cutting elements, according to an embodiment of the present disclosure.

DETAILED DESCRIPTION

The illustrations presented herein are not actual views of any particular earth-boring tool, drill bit, cutting element, or component of such a tool or bit, but are merely idealized representations which are employed to describe embodiments of the present disclosure.

As used herein, the term “earth-boring tool” means and includes any tool used to remove formation material and form a bore (e.g., a wellbore) through the formation by way of removing the formation material. Earth-boring tools include, for example, rotary drill bits (e.g., fixed-cutter or “drag” bits and roller cone or “rock” bits), hybrid bits including both fixed cutters and roller elements, coring bits, percussion bits, bi-center bits, reamers (including expandable reamers and fixed-wing reamers), and other so-called “hole-opening” tools, etc.

As used herein, the term “cutting element” means and includes any element of an earth-boring tool that is used to cut or otherwise disintegrate formation material when the earth-boring tool is used to form or enlarge a bore in the formation.

As used herein, the term “polish,” and any derivative thereof, when used to describe a condition of a surface of a volume of superabrasive material or a substrate of a cutting element, means and includes any of the methods and/or processes disclosed herein to provide a surface having a surface finish roughness less than about 10 $\mu\text{in.}$ (about 0.254 μm) root mean square (RMS) (all surface finishes referenced herein being RMS).

FIG. 1 illustrates an embodiment of an earth-boring tool of the present disclosure. The earth-boring tool of FIG. 1 is a fixed-cutter rotary drill bit 10 having a bit body 11 that includes a plurality of blades 12 that project outwardly from the bit body 11 and are separated from one another by fluid courses 13. The portions of the fluid courses 13 that extend along the radial sides (the “gage” areas of the drill bit 10) are often referred to in the art as “junk slots.” The bit body 11 further includes a generally cylindrical internal fluid plenum, and fluid passageways (not visible) that extend through the bit body 11 to an exterior surface of the bit body 11. Nozzles 18 may be secured within the fluid passageways proximate the exterior surface of the bit body 11 for controlling the hydraulics of the drill bit 10 during drilling. A plurality of cutting elements 20 is mounted to each of the blades 12.

During a drilling operation, the drill bit 10 may be coupled to a drill string (not shown). As the drill bit 10 is rotated within the wellbore, drilling fluid may be pumped down the drill string, through the internal fluid plenum and fluid passageways within the bit body 11 of the drill bit 10, and out from the drill bit 10 through the nozzles 18. Formation cuttings generated by the cutting elements 20 of the drill bit 10 may be carried with the drilling fluid through

the fluid courses **13**, around the drill bit **10**, and back up the wellbore through the annular space within the wellbore outside the drill string.

FIG. 2 is a perspective view of a cutting element **20** of the drill bit **10** of FIG. 1. The cutting element **20** includes a cutting element substrate **22** having a volume of superabrasive material, such as a diamond table **24**, disposed thereon. The diamond table **24** may comprise a polycrystalline diamond (PCD) material, having a cutting face **26** defined thereon. Superabrasive materials may also be characterized as “superhard” materials and include natural and synthetic diamond, cubic boron nitride and diamond-like carbon materials. Additionally, an interface **28** may be defined between the cutting element substrate **22** and diamond table **24**.

The diamond table **24** may be formed on the cutting element substrate **22**, or the diamond table **24** and the cutting element substrate **22** may be separately formed and subsequently attached together. The cutting element substrate **22** may be formed from a material that is relatively hard and resistant to wear. For example, the cutting element substrate **22** may be formed from and include a ceramic-metal composite material (which is often referred to as a “cermet” material). The cutting element substrate **22** may include a cemented carbide material, such as a cemented tungsten carbide material, in which tungsten carbide particles are cemented together in a metallic binder material. The metallic binder material may include, for example, cobalt, nickel, iron, or alloys and mixtures thereof. In some instances, the cutting element substrate **22** may comprise two or more pieces, one piece directly supporting the diamond table **24**, and one or more additional pieces bonded thereto. In any case, the cutting elements **20** may be secured in pockets on blades **12** as depicted in FIG. 1, such as by brazing.

While the diamond table **24** and the substrate **22** may each be generally cylindrical in shape, as shown in FIG. 2, it is to be appreciated that the substrate **22** and the diamond table **24** may each have other shapes. By way of non-limiting example, the substrate **22** and the diamond table **24** may have an elliptical shape, a triangular shape, or a non-symmetrical shape when viewed in a plane transverse to a longitudinal axis L of the cutting element **20**, as more fully described in the aforementioned U.S. Pat. No. 9,243,452, issued on Jan. 26, 2016, to DiGiovanni et al.

Referring to FIG. 2, the diamond table **24** may have a multi-chamfered edge. For example, the diamond table **24** may have a first chamfer surface **30** at a radial periphery of the diamond table **24**. A peripheral edge **32** of the first chamfer surface **30** may define a primary cutting edge of the diamond table **24**. The first chamfer surface **30** may extend radially inward from the peripheral edge **32** of the first chamfer surface **30** to a radially innermost edge **34** of the first chamfer surface **30**. A second chamfer surface **36** of the diamond table **24** may extend radially inward from a peripheral edge **38** of the second chamfer surface **36** (coincident with the radially innermost edge **34** of the first chamfer surface **30**) to a radially innermost edge **40** of the second chamfer surface **36**. In other embodiments (not shown), one or more additional chamfer surfaces may optionally be located between the peripheral edge **32** and the radially innermost edge **40**. It is to be appreciated that, while the first and second chamfer surfaces **30**, **36** are depicted as being generally straight when viewed in a longitudinal cross-sectional plane, in other embodiments (not shown), all or portions of the first and second chamfer surfaces **30**, **36** may be curved, convex, concave, or irregularly shaped when viewed in a longitudinal cross-sectional plane. Cutting ele-

ments with multiple chamfer surfaces are more fully described in the aforementioned U.S. Pat. No. 6,935,444, issued on Aug. 30, 2005, to Lund et al.; U.S. Pat. No. 6,145,608, issued on Nov. 14, 2000, to Lund et al., and U.S. Pat. No. 5,437,343, issued on Aug. 1, 1995, to Cooley et al.

A planar, flat surface **42** of the diamond table **24** may be located radially inward of the second chamfer surface **36**. The flat surface **42** may extend annularly over the cutting face **26** about the longitudinal axis L of the cutting element **20**. The flat surface **42** may extend radially inward from the radially innermost edge **40** of the second chamfer surface **36** and may be substantially transverse (i.e., perpendicular) to the longitudinal axis L of the cutting element **20**. Alternatively, the flat surface **42** may be positioned at a non-perpendicular angle with respect to the longitudinal axis L of the cutting element **20**.

A portion of the cutting face **26** radially inward of the flat surface **42** may include one or more recesses extending into the diamond table **24** toward the substrate **22**, one or more protrusions extending upward from the diamond table **24** away from the substrate **22**, or a combination thereof. The flat surface **42** and the one or more recesses and/or protrusions may be configured to manipulate the direction of flow of formation cuttings flowing over the cutting face **26** of the diamond table **24**, as more fully described in the aforementioned U.S. patent application Ser. No. 13/840,195, filed Mar. 15, 2013, now U.S. Pat. No. 9,428,966, issued on Aug. 30, 2016, to Patel et al. Additionally, the first and second chamfer surfaces **30**, **36** may operatively cooperate with the flat surface **42** and the one or more recesses and/or protrusions to manipulate the direction of formation cuttings flowing over the cutting face **26** of the diamond table **24**.

Multi-chamfer cutting elements **20** having recesses and/or protrusions in a cutting face **26** thereof, as described herein, may be fabricated using any number of techniques, including any of the techniques disclosed in the aforementioned U.S. Pat. No. 8,684,112, issued Apr. 1, 2014, to DiGiovanni et al.; U.S. Pat. No. 9,243,452, issued Jan. 26, 2016, to DiGiovanni et al.; and U.S. Pat. No. 9,482,057, issued Nov. 1, 2016, to DiGiovanni et al. For example, the cutting element **20** may be formed using a high temperature, high pressure (HTHP) process, as known in the art.

Chamfer surfaces, recessed surfaces and/or protrusions of the diamond table **24** may be formed in situ during the HTHP sintering process. Alternatively, chamfer surfaces and/or protrusions of the diamond table **24** may be formed after an HTHP sintering process. For example, a laser ablation process, as disclosed in U.S. Patent Publication No. 2009/0114628 A1, published May 7, 2009, in the name of DiGiovanni, the entire disclosure of which is incorporated herein by this reference, may be used to remove selected, localized regions of the diamond table **24**, and may be used to form chamfer surfaces, recesses and/or protrusions, as described herein, of the diamond table **24**. Additional, non-limiting examples of processes known in the art that may be utilized to assist in the formation of chamfer surfaces, recesses and/or protrusions of the diamond table **24** include an electro-discharge machining (EDM) process, a mechanical machining process, a leaching process, or any combination of the foregoing processes.

As more fully described in the aforementioned U.S. Pat. No. 9,482,057, issued Nov. 1, 2016, to DiGiovanni et al. and U.S. patent application Ser. No. 13/840,195, filed Mar. 15, 2013, now U.S. Pat. No. 9,428,966, issued Aug. 30, 2016, to Patel et al., the cumulative effect of the flat surface **42** of the cutting face **26** and a recess located radially inward of the flat surface **42** includes the inhibition or reduction of for-

mation cuttings compacting together at the cutting face **26** and forming cohesive structures (i.e., chips). When a cutting element **20** having at least one recessed surface on the cutting face **26** at a sufficient depth-of-cut is pushed through an uncut formation, granular pieces of fractured formation may be inhibited or prevented from impacting the cutting element **20** after fracturing. As a result, the granular pieces of fractured formation may not compress together sufficiently to form cohesive structures of any substantial size and may in essence be “thrown forward” from the cutting face **26** and carried away by drilling fluid as granular pieces in discrete particulate form. The ability to produce such small, granular formation cuttings is believed to reduce friction between the formation and the cutting face **26** as well as to reduce not only the amount of heat transferred to the cutting element **20** but also the Mechanical Specific Energy (MSE) of the cutting elements **20** (i.e., the amount of work performed per unit volume of rock drilled) and the power required to operate an earth-boring tool utilizing such cutting elements **20**.

Furthermore, a multi-chamfer cutting element **20** having a cutting face **26** with one or more recesses and/or protrusions associated therewith and configured as previously described allows the cutting element **20** to maintain the favorable performance characteristics discussed in the preceding paragraph while optimizing one or more of aggressiveness, durability, toughness, efficiency, and heat transfer properties of the cutting element **20**.

With continued reference to FIG. 2, such recesses and/or protrusions of the diamond table **24** may include a first recessed surface **44** extending both radially inward and longitudinally downward into the diamond table **24** from the flat surface **42**. A second recessed surface **46** of the diamond table **24** may be located radially inward of the first recessed surface **44** and may extend radially inward at an incline relative to a plane transverse to the longitudinal axis L of the cutting element **20** in a manner define a central protrusion **48** of the cutting face **26**. The central protrusion **48** may be frusto-conical and may have a top surface **49** that is flat and co-planar with the flat surface **42**, as shown; although, in other embodiments, the top surface **49** of the central protrusion **48** may be elevated or recessed in relation to the flat surface **42**. It is to be appreciated that the center of the central protrusion **48** may be radially offset from the longitudinal axis L of the cutting element **20** in a manner to impart the diamond table **24** with an asymmetrical cutting face **26**.

A radially innermost edge **50** of the first recessed surface **44** may be adjacent a peripheral edge **52** of the second recessed surface **46**. The first and second recessed surfaces **44**, **46** may together form a recess **54** in the cutting face **26** of the diamond table **24**. The recess **54** may extend annularly over the cutting face **26** about the longitudinal axis L of the cutting element **20**. In additional embodiments, the recess **54** may be defined by shapes other than an annulus. For example, as more fully described in the aforementioned U.S. Pat. No. 9,482,057, issued Nov. 1, 2016, to DiGiovanni et al., the recess **54** may be generally shaped as a square, as a regular n-sided polygon (where n may have any value from three (3) to infinity), or generally as a Reuleaux polygon (i.e., a curvilinear polygon built up of circular arcs) when viewed in a plane transverse to the longitudinal axis L of the cutting element **20**.

Referring now to FIG. 3, the first and second recessed surfaces **44**, **46** may together impart the recess **54** with a chevron shape when viewed in a cross-sectional plane containing the longitudinal axis L of the cutting element **20**, although other shapes are within the scope of the present

embodiments. The first and second chamfer surfaces **30**, **36**, the flat surface **42**, the first and second recessed surfaces **44**, **46** and the protrusion **48** may each be sized, positioned and oriented to impart the cutting element **20** with tailored performance characteristics. For example, in embodiments where the cutting element **20** is a 16 mm (about 0.630 inch or about $\frac{5}{8}$ inch) diameter cutting element, the first chamfer surface **30** may have a radial width X_1 between about 0.002 inch (about 0.051 mm) and about 0.045 inch (about 1.143 mm) measured between the peripheral edge **32** and the radially innermost edge **34** of the first chamfer surface **30** in a plane transverse to the longitudinal axis L of the cutting element **20**. Additionally, the first chamfer surface **30** may be positioned at an incline α between about 10 degrees and about 80 degrees from a plane transverse to the longitudinal axis L of the cutting element **20**.

The second chamfer surface **36** may have a radial width X_2 between about 0.002 inch (about 0.051 mm) and about 0.25 inch (about 6.35 mm) measured between the peripheral edge **38** and the radially innermost edge **40** of the second chamfer surface **36** in a plane transverse to the longitudinal axis L of the cutting element **20**. The second chamfer surface **36** may be positioned at an incline β between about 10 degrees and about 80 degrees from a plane transverse to the longitudinal axis L of the cutting element **20**.

The flat surface **42** may have a radial width X_3 between about 0.005 inch (about 0.127 mm) and about 0.125 inch (about 3.175 mm) measured between the radially innermost edge **40** of the second chamfer surface **36** and a peripheral edge of the first recessed surface **44** in a plane transverse to the longitudinal axis L of the cutting element **20**. In other embodiments, the radial width X_3 of the flat surface **42** may be greater than 0.125 inch (3.175 mm).

The first recessed surface **44** may extend radially inward and into the diamond table **24** at a decline θ between about 10 degrees and about 90 degrees measured from the flat surface **42** of the cutting face **26**.

The respective radial widths X_1 , X_2 , X_3 of the first chamfer surface **30**, the second chamfer surface **36** and the flat surface **42** may each be expressed in terms as a ratio or percentage of a radius R of the cutting element **20**. For example, in embodiments where the cutting element **20** is a 16 mm (about 0.630 inch or about $\frac{5}{8}$ inch) diameter cutter, i.e., the cutting element **20** has a radius R of 8 mm (about 0.315 inch or about $\frac{5}{16}$ inch), a radial width X_1 of the first chamfer surface **30** in the range between about 0.005 inch and about 0.045 inch may also be expressed as being in the range between about 0.01588R and about 0.14288R. Similarly, a radial width X_2 of the second chamfer surface **36** in the range between about 0.005 inch and about 0.035 inch may also be expressed as being in the range between about 0.01588R and about 0.01111R. Moreover, a radial width X_3 of the flat surface **42** in the range between about 0.005 inch and about 0.125 inch may also be expressed as being in the range between about 0.01588R and about 0.39688R.

It is to be appreciated that cutting elements **20** of sizes smaller or larger than a 16 mm diameter cutter, such as 19 mm diameter cutters and 8 mm diameter cutters, are within the scope of the embodiments disclosed herein. Furthermore, cutting elements **20** of any size may incorporate the width-to-radius ratios of the first chamfer surface **30**, the second chamfer surface **36**, and the flat surface **42**, as previously described. For example, regardless of the diameter of the cutting element **20**, the radial width X_1 of the first chamfer surface **30** may be between about 0.01588R and about 0.14288R; the radial width X_2 of the second chamfer surface **36** may be between about 0.01588R and about

0.01111R; and the radial width X_3 of the flat surface **42** may be between about 0.01588R and about 0.39688R. However, for simplicity, the distance dimensions of the cutting elements **20** described below are expressed in units of inches.

With continued reference to FIG. 3, according to one example embodiment, the first chamfer surface **30** may have a width X_1 of about 0.016 inch (about 0.406 mm) and may be positioned at an incline α of about 45 degrees from a plane transverse to the longitudinal axis L of the cutting element **20**. The second chamfer surface **36** may have a width X_2 of about 0.020 inch (about 0.508 mm) and may be positioned at an incline β of about 20 degrees from a plane transverse to the longitudinal axis L of the cutting element **20**. The flat surface **42** may have a width X_3 of about 0.031 inch (about 0.787 mm).

The inventors have performed extensive testing of various dual-chamfer cutting elements **20** using, for example, a CNC Vertical Boring Mill and have discovered that increasing the width X_2 of the second chamfer surface **36** has the effect of reducing the size of formation cuttings produced by the cutting element **20** during an earth-boring operation. Conversely, these tests have also shown that decreasing the width X_2 of the second chamfer surface **36** has the effect of increasing the size of formation cuttings produced by the cutting element **20**. Decreasing the width X_2 of the second chamfer surface **36** also increases the aggressiveness of the cutting element **20** and reduces the amount of machining required to form the cutting element **20**. The inventors' testing has also shown that reducing the width X_2 of the secondary chamfer surface **36** increases the efficiency of the cutting element **20** and increases the extent to which formation cuttings are "thrown forward" from the cutting face **26** of the cutting element **20** during an earth-boring operation. These tests have also shown that a secondary chamfer surface **36** having a width X_2 less than 0.055 inch (about 1.397 mm) may be able to absorb spalls during use that do not extend longitudinally forward and radially inward of (i.e., that do not "breach") the radially innermost edge **40** of the second chamfer surface **36**.

The aggressiveness of the cutting element **20** may also be increased by decreasing the incline β angle of the second chamfer surface **36**. By way of non-limiting example, for a more aggressive cutting element **20** relative to the previous embodiment, the second chamfer surface **36** may have a width X_2 of about 0.015 inch (about 0.381 mm) and may be positioned at an incline β of about 15 degrees from a plane transverse to the longitudinal axis L of the cutting element **20**. The aggressiveness of the cutting element **20** may be further increased by providing the second chamfer surface **36** with a width X_2 between about 0.010 inch (about 0.254 mm) and about 0.005 inch (about 0.127 mm) and an incline β angle between about 15 degrees and about 10 degrees from a plane transverse to the longitudinal axis L of the cutting element **20**.

Tests performed by the inventors have also shown that increasing the width X_3 of the flat surface **42** has the effect of reducing the MSE of the cutting element **20**. Through testing and observation, it is believed by the inventors that increasing the width X_3 of the flat surface **42** also increases the toughness of the diamond table **24** at the peripheral edge **32**. However, increasing the width X_3 of the flat surface **42** also increases the degree to which formation cuttings flow up the cutting face **26** of the cutting element **20** during an earth-boring operation.

FIG. 4 illustrates an embodiment of the cutting element **20** having a recess **54** with an arcuate cross-sectional shape in a plane containing the longitudinal axis L of the cutting

element **20**. In such an embodiment, the flat surface **42** and the central protrusion **48** may be coplanar, and an arcuate recessed surface **56** of the diamond table **24** may be located radially inward of the flat surface **42** and may have a radius R_1 between about 0.010 inch (about 0.254 mm) and about 0.40 inch (about 10.16 mm) measured in a cross-sectional plane containing the longitudinal axis L of the cutting element **20**. The arcuate recessed surface **56** may extend into the diamond table **24** at a depth Z_1 between about 0.005 inch (about 0.127 mm) and about 0.20 inch (about 0.508 mm). It is to be appreciated that, in other embodiments, the top surface **49** of the central protrusion **48** may be longitudinally elevated or recessed in relation to the flat surface **42**. In such embodiments, the depth Z_1 of the arcuate recessed surface **56** may be between about 0.005 inch (about 0.127 mm) and about 0.20 inch (about 0.508 mm) measured from either the flat surface **42** or the top surface **49** of the central protrusion **48**.

With continued reference to FIG. 4, a shape of the interface **28** between the diamond table **24** and the substrate **22** of the cutting element **20** may be configured to effectively distribute stresses caused by cutting forces and thus improve the structural integrity of the cutting element **20**. It is to be appreciated that the arcuate recessed surface **56** and the shape of the interface **28** between the diamond table **24** and the substrate **22** may each be configured as described in any of the aforementioned U.S. Pat. No. 8,684,112, issued on Apr. 1, 2014, to DiGiovanni et al.; U.S. Pat. No. 9,482,057, issued Nov. 1, 2016, to DiGiovanni et al.; and U.S. Pat. No. 9,103,174, issued Aug. 11, 2015, to DiGiovanni.

FIGS. 5 and 6 illustrate an embodiment of the multi-chamfer cutting element **20** similar to the embodiments of FIGS. 2 and 3, with a primary difference being that a second flat surface **58** extends radially inward from the radially innermost edge **50** of the first recessed surface **44** and parallel with a plane transverse to the longitudinal axis L of the cutting element **20**. The respective widths X_1 , X_2 , X_3 of the first chamfer surface **30**, the second chamfer surface **36** and the flat surface **42** may be as previously described with reference to FIGS. 2 and 3. A cutting element **20** configured as shown in FIGS. 5 and 6 has the advantage of reducing interaction of formation cuttings against the cutting face **26** because the formation cuttings impact less against the recessed second flat surface **58** than against the central protrusion **48** of the embodiments of FIGS. 2 and 3. As a result, the MSE of the cutting element **20** of FIGS. 5 and 6 is generally less than the MSE of the cutting element **20** of FIGS. 2 and 3. The inventors believe, based on their testing, that the reduced MSE of the cutting element **20** of FIGS. 5 and 6 may be advantageous for use in shale formations. Furthermore, the cutting element **20** of FIGS. 5 and 6 generally does not require additional weight-on-bit (WOB) relative to the cutting element of FIGS. 2 and 3 to achieve the substantially equivalent cutting efficiency.

Referring now to FIG. 6, in an additional embodiment, the first recessed surface **44** of the diamond table **24** may extend radially inward and into the diamond table **24** at a decline angle θ of about 10 degrees from the flat surface **42** of the cutting face **26**. In a yet additional embodiment, the first recessed surface **44** of the diamond table **24** may extend radially inward and into the diamond table **24** at a decline angle θ of about 15 degrees from the flat surface **42** of the cutting face **26**. As the decline angle θ angle of the first recessed surface **44** increases, the amount of formation cuttings interacting with the first recessed surface **44** decreases. In further embodiments, the first recessed surface **44** of the diamond table **24** may extend radially inward and

into the diamond table **24** at a decline angle θ of about 90 degrees from the flat surface **42** of the cutting face **26** to minimize formation interaction with the first recessed surface **44**. In yet other embodiments, the flat surface **42** may be located at a more peripheral location of the cutting face **26** relative to that of other embodiments by providing the first chamfer surface **30** with a width X_1 of about 0.016 inch (about 0.406 mm) and an incline angle α of about 45 degrees and the second chamfer surface **36** with a width X_2 of about 0.010 inch (about 0.254 mm) and an incline angle β of about 20 degrees. In such an embodiment, the decline angle θ of the first recessed surface may be about 12.5 degrees.

FIG. 7 illustrates an embodiment of the cutting element **20** similar to that shown in FIG. 6, wherein the cutting element **20** includes a central protrusion **48** located radially inward of and extending upwardly from the second flat surface **58**. The central protrusion **48** may be frusto-conical in shape and may have a top surface **49** substantially coplanar with the flat surface **42**. In other embodiments, the top surface **49** of the central protrusion **48** may be longitudinally elevated or recessed relative to the flat surface **42**.

In FIG. 8, the normalized results of numerous tests conducted by the inventors are provided in a graph illustrating the comparative Durability Wear Progression of a single-chamfer cutting element (labeled "Standard") and two multi-chamfer cutting elements, one of which (labeled "Dual Chamfer Large") has a secondary chamfer width X_2 nearly twice as large as the other (labeled "Dual Chamfer Small"). The "Standard" single-chamfer cutting element had a chamfer with a radial width of about 0.016 inch (about 0.406 mm) measured in a plane transverse to a longitudinal axis L of the cutting element. The "Dual Chamfer Small" cutting element **20** had a first chamfer surface **30** with a width X_1 of about 0.010 inch (about 0.254 mm) and an incline angle α of about 45 degrees and a second chamfer surface **36** with a width X_2 of about 0.014 inch (about 0.356 mm) and an incline angle β of about 20 degrees. The "Dual Chamfer Large" cutting element **20** had a second chamfer surface **36** with a width X_2 of about 0.026 inch (about 0.660 mm) and was otherwise the same as the "Dual Chamfer Small" cutting element **20**. The growth of a "Wear Scar Area," also known in the art as a "wear flat," was measured for each of the subject cutting elements, as shown on the Y-axis, versus a cutting distance of each of the subject cutting elements, as shown on the X-axis. The average point of failure of the diamond tables **24** of the subject cutting elements is illustrated by a unique indicator shape at the terminus of the plot line of each respective cutter. The performance of each of the subject cutting elements is shown as normalized in relation to the top performing cutting element. As shown, the "Dual Chamfer Small" cutting element **20** proved to absorb a larger wear scar area and cut a greater distance prior to failure than the "Standard" single-chamfer cutting element. Additionally, the "Dual Chamfer Large" cutting element **20** proved to be significantly tougher and more durable than both the "Standard" and the "Dual Chamfer Small" cutting elements, absorbing about twice as large a wear scar area and cutting nearly 50% more distance than the "Dual Chamfer Small" cutting element **20**. The testing performed by the inventors indicates that providing a dual-chamfer to a cutting element may significantly add to the life of the cutting element. The test also indicates that increasing the width X_2 of the secondary chamfer surface **36** may further increase the durability and service life of the cutting element.

FIGS. 9 through 14 illustrate the wear observed by the inventors on the subject cutting elements charted in the

graph of FIG. 8. FIGS. 9 and 10 depict respective side and front elevation views of wear absorbed by the "Standard" single-chamfer cutting element at the point at which its diamond table failed. FIGS. 11 and 12 depict respective side and front elevation views of wear absorbed by the "Small Dual Chamfer" cutting element **20** at the point at which its diamond table **24** failed. FIGS. 13 and 14 depict respective side and front plan views of wear absorbed by the "Large Dual Chamfer" cutting element **20** at the point at which its diamond table **24** failed. The size of a wear flat **59** formed in the respective diamond tables **24** and substrates **22** of the subject cutting elements is depicted in FIGS. 9, 11 and 13. The wear flats **59** can also be seen in FIGS. 10, 12 and 14, as can the sizes of a radial wear dimension, or "cutter height," originating at a cutting edge of the respective cutting elements and progressing through the diamond tables **24** and into the substrates. Spalls **59'** formed in the diamond table **24** at the cutting edge **32** are also depicted in FIGS. 10, 12 and 14. It can be seen in FIGS. 12 and 14 that the cutter height formed in the diamond tables **24** of the dual-chamfered cutting elements **20** extend radially through the first chamfer surface **30** and into the second chamfer surface **36** but do not breach the radially innermost edge **40** of the second chamfer surface **36**. Conversely, as shown in FIG. 10, the cutter height breached a radial innermost edge **34'** of the single-chamfer cutting element. As shown in FIGS. 9 through 14, the cutter height and the wear flat **59** absorbed by the "Dual Chamfer Small" cutting element at the point of diamond table failure are each greater than those absorbed by the "Standard" single-chamfer cutting element. Furthermore, the cutter height and the wear flat absorbed by the "Dual Chamfer Large" cutting element at the point of diamond table failure are each greater than those absorbed by the "Dual Chamfer Small" cutting element and the "Standard" single-chamfer cutting element.

FIG. 15 illustrates an additional embodiment of a multi-chamfer cutting element **20**. The cutting element **20** of FIG. 15 may be configured similarly to the cutting element **20** depicted in FIGS. 2 and 3, with a difference being that the central protrusion **48** may be conical in shape. In this embodiment, the central protrusion **48** may have an apex **60** extending longitudinally above the flat surface **42** of the diamond table **24** a distance H_1 between about 0.010 inch (about 0.254 mm) and about 0.50 inch (about 12.7 mm). The apex **60** of the conical central protrusion **48** may be rounded at a radius R_2 between about 0.010 inch (about 0.254 mm) and about 0.25 inch (about 6.35 mm).

FIG. 16 illustrates a further embodiment of the multi-chamfer cutting element **20** similar to the embodiment of FIG. 15, wherein the flat surface **42** extends radially inward and is adjacent with a peripheral edge **52** of the central protrusion **48**.

It is to be appreciated that the cutting face **26** of the multi-chamfer cutting elements **20** disclosed herein may include any number of shaped features, including any combination of the protrusions and/or recesses described in any of the aforementioned U.S. Pat. No. 8,684,112, issued on Apr. 1, 2014, to DiGiovanni et al.; U.S. Pat. No. 9,482,057, issued Nov. 1, 2016, to DiGiovanni et al.; U.S. Pat. No. 9,103,174, issued Aug. 11, 2015, to DiGiovanni; U.S. Pat. No. 9,243,452, issued Jan. 26, 2016, to DiGiovanni et al.; and U.S. patent application Ser. No. 13/840,195, filed Mar. 15, 2013, published as U.S. Pat. No. 9,428,966, issued Aug. 30, 2016, to Patel et al.

It is also to be appreciated that one or more of the surfaces of the cutting face **26** may be polished to have a surface finish roughness less than about 10 μm . (about 0.254 μm)

root mean square (RMS) and as low as about 0.3 μm . (0.00762 μm) or lower using any of the methods described in the aforementioned U.S. Pat. No. 8,991,525, issued Mar. 31, 2015, to Bilen et al. and also further described in U.S. patent application Ser. No. 13/840,195, filed Mar. 15, 2013, published as U.S. Pat. No. 9,428,966, issued Aug. 30, 2016, entitled "Cutting Elements for Earth-Boring Tools, Earth-Boring Tools Including Such Cutting Elements, and Related Methods," the entire disclosure of which is incorporated herein by this reference. For example, all or a portion of the first chamfer surface **30** and/or the second chamfer surface **36** may be polished to a surface finish roughness less than about 10 μm . (about 0.254 μm).

As shown in FIG. 17, a cutting element **20** is depicted configured similarly to the cutting element **20** of FIGS. 5 and 6. The entire flat surface **42** of the diamond table **24** may be polished to a surface finish roughness less than about 10 μm . (about 0.254 μm) to prevent formation cuttings from compacting together at the flat surface **42** and forming cohesive structures as the cutting element **20** engages formation material. In other embodiments, a portion of the flat surface **42** less than the entire surface thereof may be polished to a surface finish roughness less than about 10 μm . (about 0.254 μm).

Additionally, predetermined portions of any of the surfaces of the cutting face **26** of the cutting elements **20** disclosed herein may be polished to a surface finish roughness less than about 10 μm . (about 0.254 μm) for the purpose of directing formation cuttings to a particular side of the cutting face **26** as the cutting element **20** engages uncut formation material, as more fully described in the aforementioned U.S. Pat. No. 8,991,525, issued Mar. 31, 2015, to Bilen et al. For example, FIG. 18 illustrates a cutting element **20** configured similarly to the cutting element FIG. 17, with the primary difference being that the flat surface **42** of the cutting element **20** in FIG. 18 is polished to a surface finish roughness less than about 5 μm . (about 0.127 μm) on a first lateral portion **62** of the flat surface **42** while a second lateral portion **64** of the flat surface **42** remains unpolished and may have a surface finish roughness between about 20 μm . (about 0.508 μm) and about 40 μm . (about 1.016 μm). The relative difference between the surface finish roughness of the first lateral portion **62** and that of the second lateral portion **64** of the flat surface **42** may be sufficient to direct a stream of formation cuttings **68** moving over the cutting face **26** toward a lateral side of the cutting face **26** corresponding to the second lateral portion **64** of the flat surface **42**.

In further embodiments, the size, shape and orientation of the surfaces of the cutting face **26** may produce two (2) discrete streams of formation cuttings flowing toward opposite sides of the cutting face **26** as the cutting element **20** engages formation material, as more fully described in the aforementioned U.S. patent application Ser. No. 13/840,195, filed Mar. 15, 2013, published as U.S. Pat. No. 9,428,966, issued as Aug. 30, 2016, to Patel et al. In such embodiments, predetermined portions of the surfaces of the cutting face **26** may be polished to a surface finish roughness less than about 10 μm . (about 0.254 μm) to allow the formation cuttings in the two (2) discrete streams to move more freely and thus prevent the formation cuttings from compacting together to form coherent structures, thereby reducing the size of formation cuttings in the two (2) discrete streams. For example, FIG. 19 illustrates a cutting element **20** configured similarly to the cutting element of FIGS. 5 and 6. The secondary chamfer surface **36** has a width X_2 of about 0.035 inch (about 0.889 mm). A region **66** of the first and second

chamfer surfaces **30**, **36** and the flat surface **42** proximate a location at which the peripheral edge **32** engages uncut formation material may be polished to a surface finish roughness less than about 10 μm . (about 0.254 μm). As the peripheral edge **32** of the first chamfer surface **30** engages formation material, the size, shape and orientation of the first and second chamfer surfaces **30**, **36** may operatively divert formation cuttings into two (2) distinct streams **68a**, **68b** flowing toward opposite sides of the cutting face **26**. The polished portion **66** of the first and second chamfer surfaces **30**, **36** and the flat surface **42** allows the formation cuttings in the two (2) discrete streams **68a**, **68b** to move more freely over the cutting face **26** and thus inhibits formation of coherent structures within the two (2) discrete streams.

In some embodiments, a depth-of-cut limiting feature on an earth-boring tool may be positioned to inhibit interaction between an uncut earth formation and a recessed or protruding surface of the diamond table **24** during earth-boring operations. For example, such a depth-of-cut limiting feature on an earth-boring tool may be one or more of an outer surface of a blade **12** of the drill bit **10** shown in FIG. 1 and a bearing block feature as described in U.S. Patent Publication No. 2010/0276200 A1, published Nov. 4, 2010, in the name of Schwefe et al., the entire disclosure of which is incorporated herein by this reference, and as also described in the aforementioned U.S. Pat. No. 9,482,057, issued Nov. 1, 2016, to DiGiovanni et al. The depth-of-cut limiting feature may be positioned to be aligned with a radially outer edge of a recessed surface or a protruding surface of the diamond table, as described herein. In view of this, uncut formation may be prevented from contacting such a recess or protrusion during drilling operations.

Performance factors, such as aggressiveness, durability, efficiency, toughness, stability, steerability, power consumption, MSE, and passivity, may be tailored and balanced by strategically placing multi-chamfer cutting elements **20** configured as described herein on the tool at selected locations. Cutting elements **20** with a relatively smaller second chamfer surface **36**, as described herein, may exhibit more aggressive cutting performance relative to conventional PDC cutting elements. Thus, performance of the cutting elements **20** may be further tailored for specific subterranean formations, such as, by way of non-limiting examples, horizontal shales or shaly sands. When harder or more interbedded formations are to be encountered, the tool design might retain a larger selection of more passive cutters, such as conventional PDC cutters or multi-chamfer cutting elements **20** with relatively larger second chamfer surfaces **36**, as described herein, in the high depth-of-cut regions of the tool, while using more aggressive cutters, such as multi-chamfer cutting elements **20** with relatively smaller second chamfer surfaces **36**, as described herein, in the lower depth-of-cut regions.

FIG. 20 is a simple cut-away, partial cross-sectional view illustrating an embodiment of an earth-boring tool utilizing selective placement of the cutting elements **20** of the present disclosure. For illustrative purposes, the earth-boring tool is the fixed-cutter rotary drill bit **10** of FIG. 1, configured as previously described, although it is to be recognized that the selective placement of embodiments disclosed herein may be incorporated on other earth-boring tools, such as reamers, hole-openers, casing bits, core bits, or other earth-boring tools.

The drill bit **10** includes a plurality of cutting elements mounted to each blade **12** of the drill bit **10**. Moreover, as understood in the art, a profile of a drill bit **10**, configured as shown in FIG. 20, may comprise a cone region **74**, a nose

15

region 76, a shoulder region 78, and a gage region 80. Cutting elements 20 located in the respective cone and nose regions 74, 76 of a blade 12 may be exposed to a greater depth-of-cut but subjected to a lesser work rate than cutting elements 20 located in other regions of the blade 12. Conversely, cutting elements 20 located in the shoulder region 78 of the blade 12 may be exposed to a higher work rate but a lesser depth-of-cut than cutting elements 20 in other regions of the blade 12. It is to be appreciated that multi-chamfer cutting elements 20 configured as described herein may be selectively located at specific regions of the blade 12 to optimize one or more desired performance characteristics. As shown in FIG. 20, multi-chamfer cutting elements 20 configured as described herein may be selectively located in the cone region 74 and the nose region 76, and may have first and second chamfer surfaces 30, 36 sized and positioned for specific high depth-of cut performance characteristics, such as, by way of non-limiting example, passivity and chip flow performance. Additionally, multi-chamfer cutting elements 20 configured as described herein may be selectively located in the shoulder region 78 of the blade 12, and may have first and second chamfer surfaces 30, 36 sized and positioned for specific high work rate performance characteristics, such as aggressiveness. The gage region 80 of the blade 12 may be fitted with conventional PDC cutting elements or other cutting elements tailored for specific performance characteristics. In additional embodiments (not shown), multi-chamfer cutting elements 20 configured as described herein may be selectively located in only one of the cone region 74, nose region 76, shoulder region 78, or gage region 80, while conventional PDC cutting elements or other cutting elements tailored for specific performance characteristics may be located in the remaining regions. In yet other embodiments, multi-chamfer cutting elements 20 configured as described herein may be selectively located in any combination of the cone region 74, nose region 76, shoulder region 78, or gage region 80, with conventional PDC cutting elements or other cutting elements tailored for specific performance characteristics located in the remaining regions of the blade 12.

Additionally, referring to FIG. 21, multi-chamfer cutting elements 20 configured as described herein may be selectively located on one or more blades 12 of the drill bit 10. The drill bit 10 may be configured with multi-chamfer cutting elements 20 configured as described herein on alternating blades 12a-12c of the drill bit 10, while the remaining blades 12 may be fitted with conventional PDC cutting elements or other cutting elements tailored for specific performance characteristics. Benefits of such placement may include, among others, an optimal balance of the aggressiveness, stability and steerability of the drill bit 10. It is to be appreciated that in further embodiments, multi-chamfer cutting elements 20 configured as described herein may be selectively placed on specific blades and on specific regions of each specific blade, as described previously, to further tailor performance characteristics of the drill bit 10.

Embodiments of cutting elements of the present disclosure may be used to attain one or more of the advantages described above.

Although the foregoing description contains many specifics, these are not to be construed as limiting the scope of the present disclosure, but merely as providing certain example embodiments. Similarly, other embodiments of the disclosure may be devised which are within the scope of the present disclosure. For example, features described herein with reference to one embodiment may also be combined with features of other embodiments described herein. The

16

scope of the disclosure is, therefore, indicated and limited only by the appended claims, rather than by the foregoing description. All additions, deletions, and modifications to the devices, apparatuses, systems and methods, as disclosed herein, which fall within the meaning and scope of the claims, are encompassed by the present disclosure.

What is claimed is:

1. A cutting element for an earth-boring tool, comprising: a substrate;

a generally cylindrical side surface and a longitudinal axis parallel to the generally cylindrical side surface; and a volume of superabrasive material positioned on the substrate, the volume of superabrasive material comprising:

a cutting face comprising a generally planar, flat surface transverse to the longitudinal axis of the cutting element, the cutting face having one or more of at least one recess extending into the volume of superabrasive material and at least one protrusion extending outward from the volume of superabrasive material;

a first chamfer surface having a peripheral edge and a radially innermost edge, the peripheral edge of the first chamfer surface defining a cutting edge of the volume of superabrasive material, wherein a radial width of the first chamfer surface, measured between the peripheral edge and the radially innermost edge of the first chamfer surface in a plane transverse to the longitudinal axis of the cutting element, is between about 0.002 inch and about 0.045 inch, the first chamfer surface inclined at an angle between about 10 degrees and about 65 degrees from a plane transverse to the longitudinal axis of the cutting element;

a second chamfer surface having a peripheral edge and a radially innermost edge, the peripheral edge of the second chamfer surface located adjacent the radially innermost edge of the first chamfer surface, wherein a radial width of the second chamfer surface, measured between the peripheral edge and the radially innermost edge of the second chamfer surface in a plane transverse to the longitudinal axis of the cutting element, is between about 0.014 inch and about 0.25 inch, the second chamfer surface inclined at an angle between about 10 degrees and about 40 degrees from a plane transverse to the longitudinal axis of the cutting element, the second chamfer surface inclined at an angle less than an angle at which the first chamfer surface is inclined from a plane transverse to the longitudinal axis of the cutting element; and

wherein the generally planar, flat surface of the cutting face has a peripheral edge and a radially innermost edge, the peripheral edge of the generally planar, flat surface located adjacent the radially innermost edge of the second chamfer surface, and wherein a radial width of the generally planar, flat surface, measured between the peripheral edge and the radially innermost edge of the generally planar, flat surface in a plane transverse to the longitudinal axis of the cutting element, is between about 0.005 inch and about 0.125 inch.

2. The cutting element of claim 1, wherein the first chamfer surface is inclined at an angle between about 35 degrees and about 65 degrees from a plane transverse to the longitudinal axis of the cutting element.

17

3. The cutting element of claim 1, wherein a radial width of the second chamfer surface, measured between the peripheral edge and the radially innermost edge of the second chamfer surface in a plane transverse to a longitudinal axis of the cutting element, is between about 0.014 inch and about 0.035 inch.

4. The cutting element of claim 1, wherein the second chamfer surface is inclined at an angle between about 25 degrees and about 40 degrees from a plane transverse to the longitudinal axis of the cutting element, wherein the second chamfer surface is inclined at an angle less than an angle at which the first chamfer surface is inclined from a plane transverse to the longitudinal axis of the cutting element.

5. The cutting element of claim 1, further comprising an inclined surface of the cutting face located radially inward of the planar, flat surface of the cutting face, at least a portion of the inclined surface of the cutting face being recessed into the volume of superabrasive material in relation to the planar, flat surface of the cutting face.

6. The cutting element of claim 5, further comprising a recessed surface of the cutting face extending radially between the planar, flat surface of the cutting face and the inclined surface of the cutting face, the recessed surface of the cutting face declining inward from the planar, flat surface of the cutting face at an angle between about 10 degrees and about 90 degrees.

7. The cutting element of claim 5, further comprising a central protrusion located radially inward of the inclined surface of the cutting face, the central protrusion extending upward from the recessed surface of the cutting face.

8. An earth-boring tool, comprising:

at least one cutting element affixed to a tool body of the earth-boring tool, the at least one cutting element comprising:

a volume of superabrasive material positioned on a substrate, the volume of superabrasive material comprising:

a cutting face having one or more of at least one recess extending into the volume of superabrasive material and at least one protrusion extending outward from the volume of superabrasive material;

a first chamfer surface having a peripheral edge and a radially innermost edge, the peripheral edge of the first chamfer surface defining a cutting edge of the volume of superabrasive material, wherein a radial width of the first chamfer surface is measured between the peripheral edge and the radially innermost edge of the first chamfer surface in a plane transverse to a longitudinal axis of the at least one cutting element;

a second chamfer surface having a peripheral edge and a radially innermost edge, the peripheral edge of the second chamfer surface located adjacent the radially innermost edge of the first chamfer surface, wherein a radial width of the second chamfer surface is measured between the peripheral edge and the radially innermost edge of the second chamfer surface in a plane transverse to a longitudinal axis of the at least one cutting element; wherein the at least one cutting element located in one of a shoulder region and a gage region of a

18

profile of a face of the earth-boring tool comprises the radial width of the first chamfer surface between about 0.005 inch and about 0.016 inch, the first chamfer surface inclined at an angle between about 25 degrees and about 40 degrees from a plane transverse to the longitudinal axis of the at least one cutting element, the radial width of the second chamfer surface between about 0.014 inch and about 0.026 inch, the second chamfer surface inclined at an angle between about 10 degrees and about 15 degrees from a plane transverse to the longitudinal axis of the at least one cutting element; and

wherein the at least one cutting element located in one of a cone region and a nose region of a profile of a face of the earth-boring tool comprises the radial width of the first chamfer surface between about 0.010 inch and about 0.016 inch, the first chamfer surface inclined at an angle between about 50 degrees and about 70 degrees from a plane transverse to the longitudinal axis of the at least one cutting element, the radial width of the second chamfer surface between about 0.026 inch and about 0.035 inch, the second chamfer surface inclined at an angle between about 25 degrees and about 40 degrees from a plane transverse to the longitudinal axis of the at least one cutting element.

9. The earth-boring tool of claim 8, further comprising a first planar, flat surface of the cutting face located radially inward of the second chamfer surface, the first planar, flat surface of the cutting face oriented substantially parallel with the plane transverse to the longitudinal axis of the at least one cutting element, the first planar, flat surface of the cutting face having a radial width between about 0.015 inch and about 0.063 inch measured in a plane transverse to the longitudinal axis of the at least one cutting element.

10. The earth-boring tool of claim 9, further comprising a second planar, flat surface of the cutting face located radially inward of the first planar, flat surface of the cutting face, the second planar, flat surface of the cutting face being recessed into the volume of superabrasive material in relation to the first planar, flat surface of the cutting face.

11. The earth-boring tool of claim 10, wherein the second planar, flat surface of the cutting face is a substantially planar surface oriented transverse to the longitudinal axis of the at least one cutting element.

12. The earth-boring tool of claim 9, further comprising a central protrusion located radially inward of the second planar, flat surface of the cutting face and extending upward from the first planar, flat surface of the cutting face, wherein the central protrusion is one of conical and frusto-conical.

13. The earth-boring tool of claim 12, wherein the central protrusion has a domed apex.

14. The earth-boring tool of claim 9, wherein at least a portion of the first planar, flat surface of the cutting face has a surface finish roughness less than about 5 μin . RMS.

15. The earth-boring tool of claim 9, wherein at least a portion of one or more of the first chamfer surface and the second chamfer surface has a surface finish roughness less than about 20 μin . RMS.

* * * * *